

Technical Services Laboratory  
 Ridham Dock  
 Kemsley Fields Business Park  
 Sittingbourne Kent  
 ME9 8SR  
 01795 412362



| SITE        | SITTINGBOURNE LORRRY PARK ME10 2QB |         |          |          | For the attention of |     | Steve Palmer |     | email:  | steve.palmer@houlihans.co.uk |     |         |      |
|-------------|------------------------------------|---------|----------|----------|----------------------|-----|--------------|-----|---------|------------------------------|-----|---------|------|
| Sample Date | Plant Name                         | Ref No  | Concrete | Cem Type | Spec Cons            | MCC | W/C          | Age | Density | Mpa                          | Age | Density | Mpa  |
| 16/04/2025  | Sittingbourne                      | 261341  | PAV2     | CEMI     | 180                  | 340 | 0.45         | 7   |         | 30.7                         | 28  | 2286    | 44.1 |
| 16/04/2025  | Sittingbourne                      | 261343  | PAV2     | CEMI     | 180                  | 340 | 0.45         | 7   |         | 34.7                         | 28  | 2279    | 45.8 |
| 17/04/2025  | Sittingbourne                      | 761231  | PAV2     | CEMI     | 180                  | 340 | 0.45         | 7   |         | 33.1                         | 28  | 2322    | 46.0 |
| 24/04/2025  | Sittingbourne                      | 4610002 | PAV2     | CEMI     | 180                  | 340 | 0.45         | 7   |         | 37.3                         | 28  | 2313    | 43.3 |
| 28/04/2025  | Sittingbourne                      | 261348  | PAV2     | CEMI     | 180                  | 340 | 0.45         | 7   |         | 33.5                         | 28  | 2280    | 44.5 |
| 29/04/2025  | Sittingbourne                      | 261354  | PAV2     | CEMI     | 180                  | 340 | 0.45         | 7   |         | 30.5                         | 28  | 2292    | 43.6 |
| 30/04/2025  | Sittingbourne                      | 261358  | PAV2     | CEMI     | 180                  | 340 | 0.45         | 7   |         | 33.6                         | 28  | 2320    | 44.2 |
| 01/05/2025  | Sittingbourne                      | 261362  | PAV2     | CEMI     | 180                  | 340 | 0.45         | 7   |         | 35.7                         | 28  | 2319    | 40.4 |
| 02/05/2025  | Sittingbourne                      | 261365  | PAV2     | CEMI     | 180                  | 340 | 0.45         | 7   |         | 31.8                         | 28  | 2319    | 42.6 |
| 07/05/2025  | Sittingbourne                      | 261371  | PAV2     | CEMI     | 180                  | 340 | 0.45         | 7   |         | 32.5                         | 28  | 2305    | 40.3 |
| 08/05/2025  | Sittingbourne                      | 261374  | PAV2     | CEMI     | 180                  | 340 | 0.45         | 7   |         | 33.7                         | 28  |         |      |
| 09/05/2025  | Sittingbourne                      | 661001  | PAV2     | CEMI     | 180                  | 340 | 0.45         | 7   |         | 34.1                         | 28  |         |      |
| 14/05/2025  | Sittingbourne                      | 461011  | PAV2     | CEMI     | 180                  | 340 | 0.45         | 7   |         | 36.6                         | 28  |         |      |
| 20/05/2025  | Sittingbourne                      | 261395  | PAV2     | CEMI     | 180                  | 340 | 0.45         | 7   |         | 40.1                         | 28  |         |      |
| 21/05/2025  | Sittingbourne                      | 261399  | PAV2     | CEMI     | 180                  | 340 | 0.45         | 7   |         | 38                           | 28  |         |      |
| 23/05/2025  | Sittingbourne                      | 261404  | PAV2     | CEMI     | 180                  | 340 | 0.45         | 7   |         | 37.1                         | 28  |         |      |

08/05/2025 Page 1 of 1

Kevin Sharpe MICT Quality Manager (kevin.sharpe@brettconcrete.co.uk), 07739 600663

N.B, these results were sampled as part of the Brett Concrete conformity testing regime