

Technical Services Laboratory  
 Ridham Dock  
 Kemsley Fields Business Park  
 Sittingbourne Kent  
 ME9 8SR  
 01795 412362



SITE				For the attention of		Steve Palmer		email: <a href="mailto:steve.palmer@houlihans.co.uk">steve.palmer@houlihans.co.uk</a>					
Sample Date	Plant Name	Ref No	Concrete	Cem Type	Spec Cons	MCC	W/C	Age	Density	Mpa	Age	Density	Mpa
16/04/2025	Sittingbourne	261341	PAV2	CEMI	180	340	0.45	7		30.7	28	0	0
16/04/2025	Sittingbourne	261343	PAV2	CEMI	180	340	0.45	7		34.7	28	0	0
17/04/2025	Sittingbourne	761231	PAV2	CEMI	180	340	0.45	7		33.1	28	0	0
24/04/2025	Sittingbourne	4610002	PAV2	CEMI	180	340	0.45	7		37.3	28	0	0
28/04/2025	Sittingbourne	261348	PAV2	CEMI	180	340	0.45	7		33.5	28	0	0
29/04/2025	Sittingbourne	261354	PAV2	CEMI	180	340	0.45	7		30.5	28	0	0
30/04/2025	Sittingbourne	261358	PAV2	CEMI	180	340	0.45	7		33.6	28	0	0
01/05/2025	Sittingbourne	261362	PAV2	CEMI	180	340	0.45	7		35.7	28	0	0

08/05/2025 Page 1 of 1

Kevin Sharpe MICT Quality Manager (kevin.sharpe@brettconcrete.co.uk), 07739 600663

N.B, these results were sampled as part of the Brett Concrete conformity testing regime