

Technical Services Laboratory
 Ridham Dock
 Kemsley Fields Business Park
 Sittingbourne Kent
 ME9 8SR
 01795 412362



SITE	SITTINGBOURNE LORRRY PARK ME10 2QB			For the attention of		Steve Palmer		email:	steve.palmer@houlihans.co.uk				
Sample Date	Plant Name	Ref No	Concrete	Cem Type	Spec Cons	MCC	W/C	Age	Density	Mpa	Age	Density	Mpa
16/04/2025	Sittingbourne	261341	PAV2	CEMI	180	340	0.45	7		30.7	28	0	0
16/04/2025	Sittingbourne	261343	PAV2	CEMI	180	340	0.45	7		34.7	28	0	0
17/04/2025	Sittingbourne	761231	PAV2	CEMI	180	340	0.45	7		33.1	28	0	0

25/04/2025 Page 1 of 1

Kevin Sharpe MICT Quality Manager (kevin.sharpe@brettconcrete.co.uk), 07739 600663

N.B, these results were sampled as part of the Brett Concrete conformity testing regime