

Laboratory:
Unit 4
Rose Lane Industrial Estate
Lenham Heath
Kent ME17 2JN
01622 851176
XtraTec are a trading name of ACS Testing Ltd



TEST REPORT

Report No: **XTC 26637B**
Page 1 of 1

COMPRESSIVE STRENGTH AND DENSITY OF CONCRETE CUBE SPECIMENS

Method: BS EN 12390-1:2021
BS EN 12390-2:2019
BS EN 12390-3:2019
BS EN 12390-7:2019

CLIENT	Houlihans
SITE	Countrystyle Recycling, Gas Road, Milton, Sittingbourne
LOCATION	Milton Lorry Car Park
MATERIAL	PAV2, CEMI, 20mm, AEA
DATE CAST	24 April 2025
DATE RECEIVED	24 April 2025
CONCRETE SAMPLING	Sampled in accordance with BS EN 12350-1:2019 Composite Sample
CUBE STORAGE/TRANSPORATION	Cubes transported back* Deviation from BS EN 12390-2:2019
CONDITION OF CUBE ON RECIEPT	Received in cube mould
VOLUME DETERMINATION METHOD	Measured size
CURING CONDITIONS	Cube cured in tanks maintained at 18-22°C

Lab Reference	Client Ref	Date Tested	Age (Days)	Mass	Condition	Cube Dimensions			Density kg/m³	Maximum Load kN	Compressive Strength MPa
						Height	Width	Depth			
XTC 26637A	SS3	01/05/2025	7	2201.0	Saturated	100	100	100	2200	236.9	23.7
XTC 26637B	SS3	22/05/2025	28	2169.1	Saturated	99	100	100	2190	359.8	36.0
XTC 26637C	SS3	22/05/2025	28	2174.3	Saturated	100	100	100	2170	382.0	38.2

REMARKS:

ISSUE TO: Houlihans J2 - Brooklands Close Sunbury On Thames Surrey TW16 7DX	DATE: 23 May 2025
	AUTHORISED BY: D Joyce Laboratory Manager