

Laboratory:
Unit 4
Rose Lane Industrial Estate
Lenham Heath
Kent ME17 2JN
01622 851176
XtraTec are a trading name of ACS Testing Ltd



TEST REPORT

Report No: **XTC 26838A**
Page 1 of 1

COMPRESSIVE STRENGTH AND DENSITY OF CONCRETE CUBE SPECIMENS

Method: BS EN 12390-1:2021
BS EN 12390-2:2019
BS EN 12390-3:2019
BS EN 12390-7:2019

| | |
|------------------------------|--|
| CLIENT | Houlihans |
| SITE | Countrystyle Recycling, Gas Road, Milton, Sittingbourne |
| LOCATION | Milton Lorry Car Park |
| MATERIAL | PAV2, CEMI, 20mm, AEA |
| DATE CAST | 20 May 2025 |
| DATE RECEIVED | 20 May 2025 |
| CONCRETE SAMPLING | Sampled in accordance with BS EN 12350-1:2019 Composite Sample |
| CUBE STORAGE/TRANSPORATION | Cubes transported back* Deviation from BS EN 12390-2:2019 |
| CONDITION OF CUBE ON RECIEPT | Received in cube mould |
| VOLUME DETERMINATION METHOD | Measured size |
| CURING CONDITIONS | Cube cured in tanks maintained at 18-22°C |

| Lab Reference | Client Ref | Date Tested | Age (Days) | Mass | Condition | Cube Dimensions | | | Density kg/m³ | Maximum Load kN | Compressive Strength MPa |
|---------------|------------|-------------|------------|--------|-----------|-----------------|-------|-------|---------------|-----------------|--------------------------|
| | | | | | | Height | Width | Depth | | | |
| XTC 26838A | GK4 | 27/05/2025 | 7 | 2265.4 | Saturated | 100 | 100 | 99.5 | 2280 | 366.7 | 36.7 |
| | | | | | | | | | | | |
| | | | | | | | | | | | |
| | | | | | | | | | | | |

REMARKS:

| | |
|---|---|
| ISSUE TO: Houlihans J2 - Brooklands Close Sunbury On Thames Surrey TW16 7DX | DATE: 28 May 2025 |
| | |
| | AUTHORISED BY: D Joyce Laboratory Manager |